

## 'O' RING FLUID COMPATIBILITY GUIDE - L's

CHEMICAL/ MEDIA	PERFLUORO - ELASTOMER	VITON <sup>®</sup> ETP	AFLAS <sup>®</sup> TFE/P	VITON <sup>®</sup> FKM	EPDM P.C.	BUNA-N NBR	SILICONE	FLUORO- SILICONE
Lacquer Solvents	1	4	4	4	4	4	4	4
Lacquers	1	4	4	4	4	4	4	4
Lactams (Amino Acids)	1	4	3	4	2	4	–	4
Lactic Acid (Cold)	1	1	–	1	1	1	1	1
Lactic Acid (Hot)	1	1	–	1	4	4	2	2
Lard (Animal Fats)	1	1	1	1	2	1	2	1
Lauric Acid	1	–	–	–	–	–	–	–
Lavender Oil	1	1	1	1	4	2	4	2
Lead Acetate	1	4	4	4	1	2	4	4
Lead Arsenate	1	–	–	–	–	–	–	–
Lead Azide	1	–	–	–	–	–	–	–
Lead	1	–	–	–	–	–	–	–
Lead Carbonate	1	–	–	–	–	–	–	–

**GUIDE ONLY**

**1 - recommended 2 - probably satisfactory 3 - marginal 4 - not recommended**

## 'O' RING FLUID COMPATIBILITY GUIDE - L's

CHEMICAL/ MEDIA	PERFLUORO - ELASTOMER	VITON <sup>®</sup> ETP	AFLAS <sup>®</sup> TFE/P	VITON <sup>®</sup> FKM	EPDM P.C.	BUNA-N NBR	SILICONE	FLUORO- SILICONE
Lead Chloride	1	-	-	-	-	-	-	-
Lead Chromate	1	-	-	-	-	-	-	-
Lead Dioxide	1	-	-	-	-	-	-	-
Lead Linoleate	1	-	-	-	-	-	-	-
Lead Naphthenate	1	-	-	-	-	-	-	-
Lead Nitrate	1	1	2	1	1	1	2	1
Lead Oxide, Red	1	1	1	1	1	1	-	-
Ligroin	1	1	2	1	4	1	4	1
Lime Bleach	1	1	1	1	1	1	2	1
Lime-Sulfur Solution	1	1	-	1	1	4	1	1
LINDOL Hydraulic Fluid	1	2	1	2	1	4	3	3
Linoleic Acid	1	2	1	2	4	2	2	-
Linseed Oil	1	1	1	1	3	1	1	1

**GUIDE ONLY**

**1 - recommended 2 - probably satisfactory 3 - marginal 4 - not recommended**

## 'O' RING FLUID COMPATIBILITY GUIDE - L's

CHEMICAL/ MEDIA	PERFLUORO - ELASTOMER	VITON <sup>®</sup> ETP	AFLAS <sup>®</sup> TFE/P	VITON <sup>®</sup> FKM	EPDM P.C.	BUNA-N NBR	SILICONE	FLUORO- SILICONE
Liquid Oxygen	2	4	4	4	4	4	4	4
Liquified Petroleum Gas (LPG)	1	1	2	1	4	1	3	3
Liquor	1	1	1	1	1	1	-	-
Lithium Bromide, Brine	1	-	-	-	-	-	-	-
Lithium Carbonate	1	-	-	-	-	-	-	-
Lithium Chloride	1	-	-	-	-	-	-	-
Lithium Citrate	1	-	-	-	-	-	-	-
Lithium Hydroxide	1	3	1	3	1	2	-	-
Lithium Hypochlorite	1	-	-	-	-	-	-	-
Lithium Nitrate	1	-	-	-	-	-	-	-
Lithopone	1	-	-	-	-	-	-	-
Lubricating	1	1	2	1	4	2	4	2

**GUIDE ONLY**  
 1 - recommended 2 - probably satisfactory 3 - marginal 4 - not recommended



DIRECT GASKETS LIMITED  
 UNITS 26 - 36  
 DANSOM LANE SOUTH  
 HULL  
 HU8 7LA



TELEPHONE: 01482 219655    EMAIL: info@direct-gaskets.co.uk  
 FAX: 01482 321162        WEBSITE: www.direct-gaskets.co.uk

## ‘O’ RING FLUID COMPATIBILITY GUIDE - L’s

CHEMICAL/ MEDIA	PERFLUORO - ELASTOMER	VITON <sup>®</sup> ETP	AFLAS <sup>®</sup> TFE/P	VITON <sup>®</sup> FKM	EPDM P.C.	BUNA-N NBR	SILICONE	FLURO- SILICONE
Lubricating Oils, Petroleum	1	1	1	1	4	1	4	1
Lye	1	2	1	2	1	2	2	2

### GUIDE ONLY

1 - recommended 2 - probably satisfactory 3 - marginal 4 - not recommended