



DIRECT GASKETS LIMITED
UNITS 26 - 36
DANSOM LANE SOUTH
HULL
HU8 7LA



TELEPHONE: 01482 219655
FAX: 01482 321162

EMAIL: info@direct-gaskets.co.uk
WEBSITE: www.direct-gaskets.co.uk

BLUE GARD 3700

DESCRIPTION

Blue Gard 3700 is light grey in colour.

SERVICE

Water and mild chemicals.

Max recommended temperatures : -73°C to +205°C

Max recommended temperature: SHORT TERM +371°C

Max recommended pressure : 83 BAR / 1200 PSI

These temperature and pressure guides cannot necessarily be used simultaneously and may not apply to all thicknesses.

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION



DIRECT GASKETS LIMITED
 UNITS 26 - 36
 DANSOM LANE SOUTH
 HULL
 HU8 7LA



TELEPHONE: 01482 219655 EMAIL: info@direct-gaskets.co.uk
 FAX: 01482 321162 WEBSITE: www.direct-gaskets.co.uk

TYPICAL PROPERTIES BLUE GARD 3700

| | | |
|------------------|---------------------------|--|
| Tensile Strength | Across Grain ASTM F152 | 2500 psi / 17 N/mm ² |
| Compression | ASTM F36 | 7-17% |
| Recovery | ASTM F36 | 40% |
| Creep Relaxation | ASTM F38 | 25% |
| Density | ASTM F1315 | 100 lbs/ft ³ / 1.60 grams/cm ³ |

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION