



DIRECT GASKETS LIMITED  
UNITS 26 - 36  
DANSOM LANE SOUTH  
HULL  
HU8 7LA



TELEPHONE: 01482 219655      EMAIL: [info@direct-gaskets.co.uk](mailto:info@direct-gaskets.co.uk)  
FAX: 01482 321162              WEBSITE: [www.direct-gaskets.co.uk](http://www.direct-gaskets.co.uk)

## MILLBOARD

<b><u>COLOUR:</u></b>	Beige
<b><u>TENSILE STRENGTH:</u></b>	Longitudinal Fibres - 40 kg/cm <sup>2</sup> Transversal Fibres - 30 kg/cm <sup>2</sup>
<b><u>THERMAL CONDUCTIVITY:</u></b>	400°C - 0.15 W/m. °K
<b><u>HEAT TREATMENT LOSS:</u></b>	800°C - 12%
<b><u>SHRINKAGE 1000°C (24 HRS):</u></b>	<1%
<b><u>COMPRESSIBILITY:</u></b>	10% (ASTM F36 METHOD K)
<b><u>RECOVERY:</u></b>	40%
<b><u>RECOMMENDED TEMP:</u></b>	up to +1000°C
<b><u>GENERAL PROPERTIES:</u></b>	Air & Water Resistant
<b><u>THICKNESS RANGE:</u></b>	3mm, 6mm & 12mm
<b><u>TOLERANCE - THICKNESS:</u></b>	+/- 10%
<b><u>ROLL SIZE:</u></b>	1 metre x 1 metre sheet
<b><u>TOLERANCE - ROLL SIZE:</u></b>	+/- 2.5%

**THIS INFORMATION IS FOR A GENERAL GUIDE ONLY.**

**FURTHER TECHNICAL INFORMATION IS AVAILABLE ON REQUEST.**

**ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION**