



DIRECT GASKETS LIMITED
UNITS 26 - 36
DANSOM LANE SOUTH
HULL
HU8 7LA



TELEPHONE: 01482 219655
FAX: 01482 321162

EMAIL: info@direct-gaskets.co.uk
WEBSITE: www.direct-gaskets.co.uk

PLASTIC SHIM A - 0.001" (0.025mm) to 0.015" (0.38mm)

<u>COLOUR:</u>	Various
<u>TENSILE STRENGTH:</u> (ASTM D 882)	2000kgf/cm ² Machine Direction 2600kgf/cm ² Transverse Direction
<u>ELONGATION AT BREAK (%):</u> (ASTM D 882)	125 Machine Direction 80 Transverse Direction
<u>DENSITY:</u>	1.40kg/m ²
<u>WATER ABSORPTION:</u>	0.60% (1 WEEK 24°C)
<u>RECOMMENDED TEMP:</u>	-70°C to +130°C <u>MELTING POINT:</u> 265°C
<u>GENERAL PROPERTIES:</u>	Oil, Grease & Solvent Resistant Low Water Absorption
<u>SURFACE FINISH:</u>	Plate/Plate
<u>THICKNESS RANGE:</u>	0.025mm - 0.38mm
<u>ROLL SIZE:</u>	1200mm x 610mm sheets
<u>TOLERANCE - ROLL SIZE:</u>	+/- 2.5%

THIS INFORMATION IS FOR A GENERAL GUIDE ONLY.

FURTHER TECHNICAL INFORMATION IS AVAILABLE ON REQUEST.

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION