



DIRECT GASKETS LIMITED
 UNITS 26 - 36
 DANSOM LANE SOUTH
 HULL
 HU8 7LA



TELEPHONE: 01482 219655
 FAX: 01482 321162

EMAIL: info@direct-gaskets.co.uk
 WEBSITE: www.direct-gaskets.co.uk

SAB - SELF ADHESIVE BACKING

DESCRIPTION

Double sided tissue tape, solvent acrylic adhesive

Technical Details	Units	Typical Value
Adhesive thickness	Mm	0.095
Tolerance on thickness (+/-10%)	Mm	Min 0.085 Max 0.105
Release liner type		Polythene - coated Kraft
Release liner thickness	Mm	0.115
180 degree peel adhesion	N/m	Open side: 700
	N/m	Liner side: 700
Polyester Loop Tack	N/m	Open side: 1000
	N/m	Liner side: 1000
Liner release	N/m	10
Tensile strength	N/m	1000
Elongation at Break	%	4
Shear adhesion, 1kg @ 23°C	Hours	>80
Temperature exposure short term	°C	200 < 1 min
Service temperature	°C	-40 to +140
Recommended application temperature	°C	+5 to +25
Shelf life	Months	12

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION