



DIRECT GASKETS LIMITED
UNITS 26 - 36
DANSOM LANE SOUTH
HULL
HU8 7LA



TELEPHONE: 01482 219655
FAX: 01482 321162

EMAIL: info@direct-gaskets.co.uk
WEBSITE: www.direct-gaskets.co.uk

BS7531 GRADE 'X' WIRE REINFORCED NAF

DESCRIPTION

A mild steel wire mesh reinforced, high quality asbestos free material which complies with the test requirements for BS7531 Grade X. Composed of aramid/inorganic fibres, bonded with Nitrile elastomer. The formulation gives the material good chemical stability and an excellent resistance to creep at high temperature. This material has a fine, mild steel mesh reinforcement and is graphited.

SERVICE

High temperature applications. It is suitable for: gases, oils, solvents and high pressure steam, most dilute acids and alkalis and oxygen. The mild steel wire reinforcement is particularly suitable for absorbing vibration and applications requiring a higher load bearing capacity.

Max recommended temperature : SHORT TERM 450°C

Max recommended temperature : OPERATING 350°C

Max recommended temperature : OPERATING STEAM 220°C *

Max recommended pressure : 16.4MPa / 166 BAR

These temperature and pressure guides cannot necessarily be used simultaneously and may not apply to all thicknesses. The operating temperature for non-asbestos sheet materials is related to the thickness of the material. Thinner materials offer better temperature and pressure properties.

APPROVALS/COMPLIANCE

Complies with BS specification 7531 Grade X

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION



DIRECT GASKETS LIMITED
 UNITS 26 - 36
 DANSOM LANE SOUTH
 HULL
 HU8 7LA



TELEPHONE: 01482 219655 EMAIL: info@direct-gaskets.co.uk
 FAX: 01482 321162 WEBSITE: www.direct-gaskets.co.uk

TYPICAL PHYSICAL PROPERTIES 'X' WIRE REINFORCED NAF

Thickness *		1.5mm *
Density		1.97 g/cm ³
Tensile Strength	ASTM F152	20 MPa
Compression	ASTM F36J	9%
Recovery	ASTM F36J	60%
Residual Stress	BS7531 (300°C)	29.5 MPa
Fluid Immersion (thickness increase)	ASTM Oil No. 1	1.5%
Fluid Immersion	ASTM Oil No. 3	2.5%
Fluid Immersion	ASTM Fuel B	2.2%

ALL PRESSURES AND TEMPERATURES ARE SUBJECT TO INDIVIDUAL APPLICATION